

i GENERAL DESCRIPTION

Petol PZ 480-4G is a medium functionality sucrose based polyether polyol, developed as a standard polyol for rigid polyurethane foams production.

Q TECHNICAL QUALITY CONDITIONS

| No. | Characteristics | M.U. | Values |
|-----|----------------------------|----------|----------------|
| 1 | Appearance | - | viscous liquid |
| 2 | Color | - | yellow-brown |
| 3 | Hydroxyl value | mg KOH/g | 460 - 490 |
| 4 | Viscosity, at 25 °C | cP | 6500 - 9000 |
| 5 | Water (Karl-Fischer), max. | % | 0.1 |

🧪 APPLICATIONS

- base polyol of polyol blends used in the rigid polyurethane foams production for various areas (block rigid foams, sandwich panels, pipes insulations, appliances, etc).

📄 GENERAL CHARACTERISTICS

| Specific Properties | Values |
|------------------------------------|-------------|
| Density at 25°C, g/cm ³ | 1.05 - 1.15 |
| Functionality | 4.5 |
| Average molecular weight | 530 |
| Flash point, °C, min. | 200 |

The specific properties present approximate values and contain general information, without being part of the technical quality conditions.

📦 PACKING

The product is packed in stainless steel or inner coated rail or car tanks, provided with heating coil, or in clean, dry, tightly closed drums of 220 l.

🏠 STORAGE

Because it is hygroscopic and sensitive to exposure to air/light, the product will be kept in the original packaging or in storage vessels under nitrogen blanket, in cold, dry, vented areas, far from heat, moisture , direct sunlight and inconsistent materials, at temperatures between +20°C and +30°C.

🚚 TRANSPORT

ADR: Petol PZ 480-4G is not classified under ADR regulations.

RID: Petol PZ 480-4G is not classified under RID regulations.

Maritime transport IMDG: Petol PZ 480-4G is not classified under IMDG regulations.

! Methods for measuring the technical characteristics are available on request

All informations contained in this product data sheet is provided for your consideration, research and verification. For a better suitability of the product to your purpose, we recommend you carry out tests before using the product. We advise you to have your own decisions regarding safety, proper handling, storage, use and disposal. We expressly disclaim any liability for any loss, damage or expense resulting from reliance on the information provided herein. For more information, please refer to our safety data sheet.